

# Bona Quick

## WATERBORNE PRIMER

Gel primer with light wood colouration.



1K waterborne primer has a gel-like consistency and high viscosity.

Bona Quick should be used as the first coat on untreated wood without following abrasion, or in between coats of finish to reduce abrasion scratches, and fill small irregularities. It typically produces a light wood colouration, but the final colour will depend on the topcoat.

- Fast-drying gel
- Reduces scratches
- First layer or in-between coats
- Safe and easy application

# Bona Quick

## WATERBORNE PRIMER

**Gel primer with light wood colouration.**

### TECHNICAL DATA

<b>Product type / base:</b>	1-component waterborne trowel primer
<b>Solids content:</b>	approx. 40%
<b>Dilution:</b>	Do not dilute.
<b>Drying time:</b>	20-30 minutes (20°C/60% R.H)
<b>Application tools:</b>	Stainless steel trowel
<b>Application rate:</b>	On untreated wood: 25-35 m <sup>2</sup> /L (≈30-40 g/m <sup>2</sup> ) per coat Between coats: approx. 50 m <sup>2</sup> /L (≈20 g/m <sup>2</sup> )
<b>Giscode:</b>	W2+
<b>Safety:</b>	Unclassified
<b>Cleaning:</b>	Wipe tools free from residual material before cleaning with a minimum of water, dried material can be removed with acetone, dispose of all waste at an approved waste disposal facility - do not pour down drains or sewers.
<b>Shelf life:</b>	1 year from date of production in unopened original container.
<b>Storage/Transport:</b>	The temperature must not fall below +5°C or exceed +30°C during storage and transport. Store in a cool place.
<b>Disposal:</b>	Containers with a minimal amount of dried material may be recycled. All waste must be disposed of at an approved waste disposal facility - do not pour down drains or sewers. Follow all local waste regulations.
<b>Pack size:</b>	5 litre can.
<b>Certificates &amp; standards:</b>	GREENGUARD

*Additional detailed information is noted in the appropriate Safety Data Sheet.*

### PREPARATION

Ensure the floor is acclimatised to its end-use environment. The surface must be sanded back to bare wood, dry and free from sanding dust, oil, wax and other contamination. Sanding with a 120 grit abrasive using a Bona Quattro Disc, or similar equipment is recommended for the final sanding of the wood.

Allow the product to reach room temperature. Optimal application conditions are between 18-25°C and 30-60% relative humidity. High temperatures and low humidity shorten, low temperatures and high humidity lengthen drying time. **Minimum temperature for use is 13°C.**

# Bona Quick

## WATERBORNE PRIMER

Gel primer with light wood colouration.

### TREATMENT SCHEDULE

#### Typical treatment schedule:

Untreated wood:

3× Bona Quick

2× Bona Lacquer

Between coats of lacquer:

1-2× Bona Quick

### APPLICATION

1. Apply the primer using a stainless-steel trowel. Ensure that no strings of primer are left behind.
2. Allow to dry and then apply a second layer in the opposite direction to the first layer.
3. Let dry and apply a third and final layer.

Normally no grain raising occurs and abrading is therefore unnecessary. If a mid-abrasion is required, then this should be done after the first coat of lacquer and not directly on Bona Quick.

### IMPORTANT!

Bona Quick should never be used as the final treatment for wood floors.

The information in this document and all other advice and recommendations that we provide to help and assist the applicator are based on previous experience and extensive testing but makes no claim to be complete. Because of the wide range of possible uses and conditions of application of our products, we do not relieve users from the need to carry out their own trials or to seek technical advice from Bona before use. Bona can only guarantee its products and not the construction as a whole. Observe recommendations from flooring manufacturer and the provisions of relevant standards.